

REPORT OF TESTING

Serial No. : 06/MCI.AHK/IV/ 25

Date of Received : 10/09/2025

Date of Test : 11/09/2025

Page : 1 of 1

Product & Type : GLUE & MUF
Quantity/Size/Thickness : 18.0mm (13Ply)
Description / Condition of Sample : Wrapped by Plastic
Tested for : Bending Strength & modulus of elasticity
Standard Test Method : EN 310 Structural Plywood
Company : KOSMEX COMPANY LIMITED
Address : No 5, Lane 205/37/26 Xuan Dinh Street, Xuan Dinh Ward, Bac Tu Liem District, Hanoi, Vietnam
Lot. No. : Sample Plywood
Supplier Sample : Product Certification Dept. (HIEU)
Sampling Method : -
Sample Purpose : Daily testing
TEST RESULT:

Sample Code	Bending Strength & Average static bending			
	Bending Strength(MPa)		Average static bending strength(MPa)	
18.0mm	Transverse 0°	Longitudinal 90°	Transverse 0°	Longitudinal 90°
	49	47.3	6470	5670

Place and date of issue, Ha Noi September 11, 2025



T.P NGUYỄN TIẾN THÀNH

This Certificate may not be reproduced Except in full, without written approval of the Company.

This Certificate refer to the tested sample only. All tests are carried out to the best of our knowledge and ability and our responsibility is limited to the correctness of the result. This certificate is issued on the understanding that it does not relieve parties concerned from their contractual obligation.